



Plibrico Company, LLC

1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Technical Data Sheet Pliflow HyMOR 90 KK

Product # 14801

Available Internationally As:

Plico Flow LC 90 KK

Product Description:

A 90% alumina, self leveling, low cement castable.

Standard Packaging: 55 # / 25 kg Bag

Shelf Life: 6 months

Service Limit: 3100 °F 1700 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 185 pcf 2964 kg/m³

Bulk Density - To Place: 185 pcf 2964 kg/m³

Minimum Time To Firing: 24 hr

Abrasion Loss after 1500°F / 815°C per ASTM C704

4 cc

Chemistry (calcined) %					
Al ₂ O ₃	91.4	Alk	0.5	MgO	0.1
SiO ₂	6.4	TiO ₂		ZrO ₂	
CaO	1.6	P ₂ O ₅		Other	
Fe ₂ O ₃	0.1	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min	5.2	1.4	1.3
	max	6.2	1.6	1.6
Pumping	min			
	max			

Coefficient of Thermal Expansion (reversible):

5.4 x 10⁻⁶ in/in/°F / 9.7 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	27.5	4.0
1000°F / 540°C	22.8	3.3
1500°F / 815°C	20.0	2.9
2000°F / 1090°C	20.3	2.9

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	0.0	9500	66.0	2000	13.8		
1500	820	-0.3	10000	69.0	3000	20.7	4000	27.6
2500	1370	-0.6			4000	27.6	1000	6.9
3000	1650	-0.7			4500	31.0		

Other Data:

Release Date: 1 Aug 2019

Heat Up Guide: Schedule C or C-Linear

ASTM Class: C 401 Class F

Low Cement Castable

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.