



Plibrico Company, LLC

1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Technical Data Sheet

Plibrico 90 AB

Product # 10090

Available Internationally As:

Plico 90 AB

Product Description:

A 90% alumina, air bonded plastic refractory.

Standard Packaging: 55 # / 25 kg Carton

Shelf Life: 12 months

Service Limit: 3400 °F 1870 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 172 pcf 2755 kg/m³

Bulk Density - To Place: 190 pcf 3044 kg/m³

Minimum Time To Firing: 0 hr

Abrasion Loss after 1500°F / 815°C
 per ASTM C704

N/A cc

Chemistry (calcined) %					
Al ₂ O ₃	89.9	Alk	0.2	MgO	0.1
SiO ₂	7.7	TiO ₂	1.1	ZrO ₂	
CaO		P ₂ O ₅		Other	
Fe ₂ O ₃	1.1	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min			
	max			
Pumping	min			
	max			

Coefficient of Thermal Expansion (reversible):

5.0 x 10⁻⁶ in/in/°F / 9.0 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	16.7	2.4
1000°F / 540°C	15.1	2.2
1500°F / 815°C	14.1	2.0
2000°F / 1090°C	14.3	2.1

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	-0.5	2200	15.0	900	6.2		
1500	820	-0.6	3500	24.0	1400	9.7	1800	12.4
2000	1090	-0.7			2000	13.8	2000	13.8
2500	1370	-0.3			2300	15.9	900	6.2
3000	1650	-0.7			2800	19.3		

Other Data: Material ordered in either Stiff (SF), Standard (SD), or Export (EX) workability.

Release Date: 1 Aug 2019

Heat Up Guide: Schedule A

ASTM Class: C 673 90% Alumina Plastic Refractory

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.