



Plibrico Company, LLC

1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Technical Data Sheet Pligun Fast Track 80-31 AI

Product # 3255

Available Internationally As: Plico Gun Mix Fast Track 80-31 AI

Product Description:

An 80% alumina, non wetting, low cement gun mix. Designed for typical aluminum melting and holding furnace applications including hot and cold maintenance of worn aluminum areas and upper sidewalls

Standard Packaging: 55 # / 25 kg Bag

Shelf Life: 9 months

Service Limit: 3100 °F 1700 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 158 pcf 2531 kg/m³

Bulk Density - To Place: 158 pcf 2531 kg/m³

Minimum Time To Firing: 4 hr

Abrasion Loss after 1500°F / 815°C
 per ASTM C704

9 cc

Chemistry (calcined) %					
Al ₂ O ₃	81.7	Alk	0.2	MgO	0.1
SiO ₂	12.7	TiO ₂	1.6	ZrO ₂	
CaO	2.0	P ₂ O ₅		Other	
Fe ₂ O ₃	1.5	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min			
	max			
Pumping	min			
	max			

Coefficient of Thermal Expansion (reversible):

3.9 x 10⁻⁶ in/in/°F / 7.0 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	11.1	1.60
1000°F / 540°C	9.6	1.38
1500°F / 815°C	9.3	1.34
2000°F / 1090°C	10.2	1.47

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	-0.1	7500	52.0	1800	12.4		
1500	820	-0.4	6500	45.0	1500	10.3		

Other Data:

Release Date: 1 Aug 2019

Heat Up Guide: Schedule C or C-Linear

ASTM Class: C 401 Class F

Low Cement Castable

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.