



Plibrico Company, LLC

1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Technical Data Sheet Plicast Al-Shield GHC 8 C KK

Product # 20056

Available Internationally As: Plico Castable AS GHC 8 C KK

Product Description:

An 80% alumina, coarse grain aluminum resistant, low cement castable with excellent resistance to thermal cycling, impact and fracture.

Standard Packaging: 1400 # / 636 kg Super Sack

Shelf Life: months

Service Limit: 3000 °F 1650 °C

Contact Limit: 2000 °F 1090 °C

Bulk Density - In Service: 172 pcf 2755 kg/m³

Bulk Density - To Place: 172 pcf 2755 kg/m³

Minimum Time To Firing: 16 hr

Abrasion Loss after 1500°F / 815°C
 per ASTM C704

5 cc

Chemistry (calcined) %					
Al ₂ O ₃	77.4	Alk	0.2	MgO	
SiO ₂	10.2	TiO ₂	1.2	ZrO ₂	
CaO	2.1	P ₂ O ₅		Other	7.7
Fe ₂ O ₃	1.1	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min	5.3	35.7	33.7
	max	6.0	40.4	38.2
Casting	min	6.0	40.4	38.2
	max	6.7	45.1	42.7
Pumping	min			
	max			

Coefficient of Thermal Expansion (reversible):

4.4 x 10⁻⁶ in/in/°F / 7.9 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	15.7	2.3
1000°F / 540°C	15.3	2.2
1500°F / 815°C	14.8	2.1
2000°F / 1090°C	15.5	2.2

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	0.0	10000	69.0	2200	15.2		
1500	820	-0.2	11000	76.0	1900	13.1	3200	22.1

Other Data:

Release Date: 27 Jan 2017

Heat Up Guide: Schedule AT AS or AT AS

ASTM Class: C 401 Class E Low Cement Castable

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.