



Plibrico Company, LLC

1935 Techny Road - Unit 16
Northbrook, IL 60062
(312) 337-9000
www.plibrico.com

Technical Data Sheet Plicast Si-Bond SD

Product # 14780

Available Internationally As: Plico Castable Si-Bond SD

Product Description:

A super duty, high hot strength, cement free castable with excellent alkali and acid resistance.

Standard Packaging: 55 # / 25 kg Bag

Shelf Life: 4 months

Service Limit: 2900 °F 1590 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 145 pcf 2323 kg/m³

Bulk Density - To Place: 145 pcf 2323 kg/m³

Minimum Time To Firing: 24 hr

Abrasion Loss after 1500°F / 815°C
per ASTM C704

N/A cc

Chemistry (calcined) %					
Al ₂ O ₃	49.2	Alk	0.5	MgO	0.1
SiO ₂	47.5	TiO ₂	1.8	ZrO ₂	
CaO	0.2	P ₂ O ₅		Other	
Fe ₂ O ₃	0.8	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min	5.3	1.4	1.3
	max	6.4	1.7	1.6
Pumping	min			
	max			

Coefficient of Thermal Expansion (reversible):

3.0 x 10⁻⁶ in/in/°F / 5.4 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	7.9	1.1
1000°F / 540°C	8.1	1.2
1500°F / 815°C	8.3	1.2
2000°F / 1090°C	8.6	1.2

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
		0.0	2000	14.0	475	3.3		
		-0.1	2500	17.0	500	3.4	900	6.2
		-0.2			1000	6.9	1800	12.4
		-0.3			2200	15.2	2500	17.2
		0.2			2700	18.6	900	6.2

Other Data:

Release Date: 1 Aug 2019

Heat Up Guide: Schedule E

ASTM Class: C 401 Class E No Cement Castable

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.