



# Plibrico Company, LLC

1935 Techny Road - Unit 16  
 Northbrook, IL 60062  
 (312) 337-9000  
 www.plibrico.com

# Technical Data Sheet

## Pligun 3000

Product # 2336

Available Internationally As:

Plico Gun Mix 3000

### Product Description:

A super duty, low cement refractory gun mix.

**Standard Packaging:** 55 # / 25 kg Bag

**Shelf Life:** 9 months

**Service Limit:** 3000 °F 1650 °C

**Contact Limit:** N/A °F N/A °C

**Bulk Density - In Service:** 128 pcf 2051 kg/m<sup>3</sup>

**Bulk Density - To Place:** 128 pcf 2051 kg/m<sup>3</sup>

**Minimum Time To Firing:** 16 hr

### Abrasion Loss after 1500°F / 815°C per ASTM C704

N/A cc

### Chemistry (calcined) %

Al <sub>2</sub> O <sub>3</sub>	47.9	Alk	0.7	MgO	0.2
SiO <sub>2</sub>	46.1	TiO <sub>2</sub>	1.8	ZrO <sub>2</sub>	
CaO	2.5	P <sub>2</sub> O <sub>5</sub>		Other	
Fe <sub>2</sub> O <sub>3</sub>	0.9	SiC			

### Coefficient of Thermal Expansion (reversible):

2.9 x 10<sup>-6</sup> in/in/°F / 5.2 x 10<sup>-6</sup> mm/mm/°C

### Thermal Conductivity

Temperature	btu*in/hr*ft <sup>2</sup> *°F	W/m°C
500°F / 260°C	6.4	0.9
1000°F / 540°C	6.5	0.9
1500°F / 815°C	6.7	1.0
2000°F / 1090°C	7.2	1.0

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min			
	max			
Pumping	min			
	max			

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110	-0.1	2000	14.0	800	5.5		
1500	820	-0.3	1800	12.0	600	4.1	800	5.5
2000	1090	-0.2			500	3.4	700	4.8
2500	1370	1.2			800	5.5	250	1.7
3000	1650	-0.9			1700	11.7		

Other Data:

Release Date: 1 Aug 2019

Heat Up Guide: Schedule B

ASTM Class: C 401 Class E Low Cement Castable

Refractory material should be stored in a cool, dry environment.

**Note:** All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.