



Plibrico Company, LLC

1935 Techny Road - Unit 16
 Northbrook, IL 60062
 (312) 337-9000
 www.plibrico.com

Technical Data Sheet

Plistix SR-90

Product # 12020

Available Internationally As:

Plico Stix SR-90

Product Description:

A high alumina, based, phosphate bonded, plaster type refractory servicing mix. Non wetting to aluminum alloys.

Standard Packaging: 50 # / 23 kg Pail

Shelf Life: 3 months

Service Limit: 3300 °F 1820 °C

Contact Limit: N/A °F N/A °C

Bulk Density - In Service: 160 pcf 2563 kg/m³

Bulk Density - To Place: 175 pcf 2804 kg/m³

Minimum Time To Firing: 0 hr

Abrasion Loss after 1500°F / 815°C
per ASTM C704

N/A cc

Chemistry (calcined) %					
Al ₂ O ₃	87.7	Alk	0.2	MgO	0.1
SiO ₂	7.6	TiO ₂	0.6	ZrO ₂	
CaO	0.1	P ₂ O ₅	2.7	Other	
Fe ₂ O ₃	0.7	SiC			

Water Range Per Standard Package		%	Quarts	Liters
Vib Casting	min			
	max			
Casting	min			
	max			
Pumping	min			
	max			

Coefficient of Thermal Expansion (reversible):

4.9 x 10⁻⁶ in/in/°F / 8.8 x 10⁻⁶ mm/mm/°C

Thermal Conductivity	btu*in/hr*ft ² *°F	W/m°C
500°F / 260°C	17.1	2.46
1000°F / 540°C	15.4	2.22
1500°F / 815°C	14.4	2.07
2000°F / 1090°C	14.5	2.09

Temperature		Linear Change% per ASTM C113	CCS per ASTM C133		Cold MOR per ASTM C133		Hot MOR per ASTM C583	
°F	°C		psi	MPa	psi	MPa	psi	MPa
230	110		1250	9.0				

Other Data:

Release Date: 1 Aug 2019

Heat Up Guide:

ASTM Class: C 673 90% Alumina

Refractory material should be stored in a cool, dry environment.

Note: All data are averaged results of ASTM tests (where applicable) on laboratory specimens. Reasonable variations in data can be expected. Data is not to be used for specification purposes. Product data is periodically updated to reflect product, raw material, process and/or testing changes. Please consult your Plibrico representative to make sure you have the most current data.